

Basis	Putty for eablock® K
Resin	Putty for eablock K Comp. A
Hardener	Putty for eablock K Comp. B
Colour	salmon pink

Applications

- Repairing for eablock K

Properties

- very high abrasion
- very shock resistant
- very well workable

Processing data

Product		Mixture Putty for eablock® K	Resin Putty for eablock K Comp. A	Hardener Putty for eablock K Comp. B
Colour		salmon pink	yellow clear	salmon pink
Mixing ratio	p. b. w.		100	100
Viscosity at 25°C	mPas	thixotrop	thixotrop	-
Density at 20°C	g / cm ³	1,34 ± 0,02	1,04 ± 0,02	1,63 ± 0,03
Pot life 200 g / 20°C	min.	20 - 30	-	-
Curing time at RT	hrs.	10 - 12	-	-

Sales units (packages)

Units	Comp. A	Putty for eablock K Comp. A	0,500 kg
	Comp. B	Putty for eablock K Comp. B	0,500 kg

Processing instructions

Before application the B-component of the repair set is to be stirred, as it is slightly filled. Mixing ratio of Comp. A and Comp. B is 1:1. Evacuation of the mixture before casting ensures a bubble-free repair.

Depending on the casting thickness the repair cures within 10 - 12 hours. A complete curing is achieved after 1-2 days at room temperature, or after 8 hours at 50-60°C.

In General

The repair compound for **eblock® K** is a two-component Polyurethane compound which is slightly filled and cures at room temperature.

The repair compound is used for after pouring of contour amendments and repair of our block **eblock® K**.

Storing

At room temperature (18 – 25°C) and closed original containers storage life is 6 months.
Partly used containers have always to be closed and the material has to be used up as soon as possible.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk