

Basis	2 - Component - Epoxy Resin, heat curing
Resin	BLH Epoxy 200
Hardener	BLH hardener W 400
Colour	greenish transparent
Further hardeners	BLH hardener W 15 / BLH hardener K 25 / BLH hardener K 30

Applications

- Hand laminating
- Boatbuilding

Properties

- hardener W 400 is miscible with hardeners W 15 and K 25
- heavy duty bonded fabrics
- excellent soaking of glass fibre cloth
- excellent soaking of carbon fibre cloth
- certified according to germanischer lloyd
- low viscosity

Processing data

Product		Mixture BLH Epoxy 200 / W 400	Resin BLH Epoxy 200	Hardener BLH hardener W 400
Colour		greenish transparent	transparent	greenish transparent
Mixing ratio	p. b. w.		100	30
Viscosity at 25°C	mPas	330 ± 80	1200 ± 200	10 ± 5
Density at 20°C	g / cm ³	-	1,15 ± 0,02	0,935 ± 0,02
Pot life 100 g / 20°C	min.	380 - 420	-	-
Pot life 500 g / 23°C	min.	270 - 310	-	-
Curing time at RT	hrs.	-	-	-
Post curing	Time in h/ Temperature in °C	10 - 12 / 70	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	110 ± 10
Flexural modulus	EN ISO 178	MPa	2700 ± 150
Tensile strength	EN ISO 527	MPa	65 ± 3
Tensile modulus	EN ISO 527	MPa	3150 ± 150
Breaking elongation (tensile)	EN ISO 527	%	9,0 ± 0,2
Compressive strength	EN ISO 604	MPa	
Heat resistance (HDT)	DIN EN ISO 75 B	°C	72 ± 2
Glass transition temperature TG	TMA	°C	80 ± 2
Shore hardness	DIN 53505	Shore D	80 ± 2
Water absorption 24 h 23° C	DIN 53495 process L	%	0,12 ± 0,01
Water absorption 168 h 23° C	DIN 53495 process L	%	0,31 ± 0,02

Sales units (packages)

Units	BLH Epoxy 200 BLH hardener W 400	can 25 kg / barrel 50 kg / barrel 200 kg / container 1000 kg can 7,5 kg / can 30 kg / barrel 180 kg
-------	-------------------------------------	--

Processing instructions

Slight discoloration of the hardener by oxygen possible, which doesn't affect the products quality.

1) Demoulding of laminates made at room temperature (20°C) is possible. The parts show very good strength. To achieve maximum property values for example for flexural strength and heat resistance, we recommend thermal treatment at the recommended temperature.

2) By additional 4 hrs. post curing at 90 – 100 °C after thermal treatment for 10 hrs. at about 70°C, a heat resistance (Tg) of more than 90°C is achieved.

Storing

At appropriate storage (room temperature) in closed original container 9 months.

Occurring crystallization, due to disadvantageous storage conditions, can be made return by warming up the material at approx. 60 °C.

Already opened containers should be closed immediately after use and also protected against moisture. Material should be used as soon as possible.

Safety measure

When processing this product the recommended protection measures of the government safety organization of the chemical industry should be followed. Safety advices should be followed.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk