

## ebacryl Styling Release Agent MK III

Release Agent for hard styling clay models when using ebacryl O-1/SP-1

**Not suitable to release an epoxy or polyester resin from hard styling clay models.**

### Characteristics

Colour:	white milky
Specific weight at 25 °C	approx. 1,0 g/cm <sup>3</sup>
Flash point (°C)	> 100
Solubility in water	soluble
Consumption (m <sup>2</sup> )	approx. 0,1 - 0,2 ltr.

### Application instructions

- \* Apply a thin film to the surface of the clay using a sponge, soft cloth or brush
- \* Allow this coat to dry then apply a second coat
- \* After the second coat has dried the ebacryl O-1/SP-1 can be applied
- \* The ebacryl Styling Release Agent MK III can be removed from the clay surface by using a soft cloth soaked in white spirit

**Packing size** 1 ltr. - bottle