

Basis	<b>glass fiber reinforced polyurethane resin</b>
Resin	<b>MG 453 GF Comp. A</b>
Hardener	<b>MG 453 Comp. B</b>
Colour	black

### Applications

- Funktional parts automotive field
- Funktional parts EPD field
- Prototyping parts EPD field
- Prototypes automotive field
- Cladding parts automotive field
- Cladding parts EPD field

### Properties

- high rigidity
- high heat resistance

### Processing data

Product		Mixture MG 453 GF / Comp. A + B	Resin MG 453 GF Comp. A	Hardener MG 453 Comp. B
Colour		black	black	brown
Mixing ratio	p. b. w.		<b>100</b>	<b>60</b>
	volume		100	61
Viscosity at 25°C	mPas	non applic.	3250 ± 250	120 ± 20
Density at 20°C	g / cm <sup>3</sup>	1,29 ± 0,02	1,24 ± 0,02	1,22 ± 0,02
Pot life at 20°C	seconds	55 - 60	-	-
Curing time at RT	min.	10 - 15	-	-
Post curing	Time in h/	4 / 70	-	-
	Temperature in °C	4 / 120		

### Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	90 ± 2
Flexural modulus	EN ISO 178	MPa	2516 ± 56
Flexural strength at breakage	EN ISO 178	%	6,2 ± 0,2
Compressive strength	EN ISO 604	MPa	66 ± 2
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	18 ± 1,6
Heat resistance (HDT)	DIN EN ISO 75 B	°C	108 ± 5
Glass transition temperature TG	DMA	°C	124 ± 5
Shore hardness	DIN 53505	Shore D	84 ± 3

### Sales units (packages)

Units	Comp. A	MG 453 GF Comp. A	20 kg
	Comp. B	MG 453 Comp. B	12 kg

## Processing instructions

It is essential to stir component A before use, as the additives tend to sedimentation. Component B has not to be stirred.

The moulding tools should be made of a polyurethane- resp. epoxy resin system, with a high-quality surface.

In order to improve the surface appearance of the component, it is possible (but no must to do!):

-to preheat the material to 30°C

-to preheat the moulds to 40 - 50°C

A combination of preheated material and moulds is the optimum.

The wall thicknesses of the components are approx. 5 mm. Ribs or bigger material accumulations can also be produced.

The shrinkage is calculated with

0,25 % - without post curing

0,65 % - with post curing

The components can be demoulded after approx. 10 min. This can differ accordingly to wall thickness and temperature.

The postcuring has to be made by means of a supporting structure.

## In General

**ebalta** MG 453 GF is processed on a two-component low pressure device.

After grinding with a sand paper , grit 280, the surface can be varnished with a commercial lacquer. For better adhesion we recommend the use of a primer coat.

Release agent – please see category release agent

## Storing

In temperierten Räumen (18 – 25°C) und ungeöffneten Originalgebinden beträgt die Lagerfähigkeit 6 Monate.

Angebrochene Gebinde sind stets zu verschließen und baldmöglichst zu verarbeiten.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT  
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk