

Basis	gel coat
Resin	OH 4
Hardener	SL
Colour	white
Further colours	blue
Further hardeners	SR

Applications

- Negatives
- Master models
- Jigs
- Foundry patterns

Properties

- versatile
- longer processing time
- very good spreadable
- impact resistant surface
- easy to grind

Processing data

Product		Mixture OH 4 / SL	Resin OH 4	Hardener SL
Colour		white	white	amber
Mixing ratio	p. b. w.		100	14
Viscosity at 25°C	mPas	thixotrope	pasty	2200 ± 450
Density at 20°C	g / cm ³	1,4 ± 0,05	1,45 ± 0,02	1,05 ± 0,02
Pot life 200 g / 20°C	min.	25 - 30	-	-
Curing time at RT	hrs.	6 - 8	-	-
Post curing	Time in h/ Temperature in °C	-	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	98 ± 5
Flexural modulus	EN ISO 178	MPa	4500 ± 300
Flexural strength at breakage	EN ISO 178	%	2,7 ± 0,4
Tensile strength	EN ISO 527	MPa	-
Tensile strength / test piece type 2	ISO 37	MPa	-
Elongation at break	ISO 37	%	-
Compressive strength	EN ISO 604	MPa	95 ± 5
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	11 ± 4
Heat resistance (Martens)	DIN 53458	°C	63 ± 3
Heat resistance (HDT)	DIN EN ISO 75 B	°C	-
Glass transition temperature TG	methode DSC	°C	-
Shore hardness	DIN 53505	Shore D	89 ± 3
Coefficient of linear expansion	DIN 53752	10 ⁻⁶ K ⁻¹	-

Sales units (packages)

Packing size	A-Pack	OH 4 / SL	resin 12 x 0,325 kg + hardener 12 x 0,046 kg = 4,452 kg
Units	Resin	OH 4	6,000 kg / 20,000 kg
	Hardener	SL	1,000 kg / 5,000 kg

Processing instructions

The temperature of material and processing should be between 18 and 25° C.

After each use the containers have to be closed again.

Porous mould surfaces should be sealed before (**ebalta** sealant).

For an optimum mould release we recommend a suitable release agent (e.g. T 1-1) which can be easily applied with a brush.

The mould should be treated 2 or 3 times with release agent and allowed to evaporate for approx. 20 min after every application.

Mixing ratio resin/hardener according to instructions!

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent.

Storing

Storage at room temperature 18-25 °C.

Already opened containers should be closed immediately after use and should be used as soon as possible.

Information about the expiration date you find on the sales packages.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk