

Technical Data Sheet

EP 679 Tooling Board Repair Paste

Contact the ebalta UK technical team for further information on this material

The EP 679 repair paste system is designed for use with blue intermediate temperature epoxy tooling boards. The resin system is carefully matched to the properties of those boards and exhibits toughened properties, as well as superior bonding properties.

Processing Data					
Property	Test Method	Value	SI Units	Value	Imp Units
Colour	Visual	Blue	-	-	-
Mixing ratio	-	100A : 21B	By weight	-	-
Mixed viscosity at 25°C	ASTM D2196	Paste	cP	-	-
Pot life at 25°C, 150g mass	-	10	minutes	-	-
Thin film gel time at 25°C	-	15	minutes	-	-

Physical Data					
Property	Test Method	Value	SI Units	Value	Imp Units
Density, cured	ASTM D792	0.65	g/cm ³	-	-
Coefficient of thermal expansion	TMA	-	-	1.8 x10 ⁻⁵	In/in/ °F
Shore hardness	ASTM D2240	68	Shore D	68	Shore D



ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
 t: +44 1332 814700 . f: +44 1332 814775 . e: info@ebalta.co.uk . w: www.ebalta.co.uk

Processing Instructions

Application and Mixing:

Boards to be repaired must be clean and free of contaminants. Part A contains fillers that are lighter than the resin. The lightweight fillers may rise to the surface of the resin. These ingredients must be thoroughly mixed before combining part A with part B. The use of a mechanical mixer is desirable. Once part A has been completely mixed add part B and thoroughly mix again. Always use clean dry tools for mixing and applying. Mix according to the mix ratio stated for the specific product. Material temperatures should not be below 65°F when mixing.

Cure Increments:

High temperature epoxy systems require an elevated temperature post cure to enable the resin and hardener to develop their full physical and temperature properties. Select one of the following cure schedules depending upon the physical properties of the master and the desired physical properties of the final tool. Please contact technical service if you find it necessary to have a different post cure schedule.

Cure Schedule	Option I	Option II
24 hrs at 77°F (25°C)	X (S)	X (S)
7 days at 77°F (25°C)	X (U)	
4 hrs at 150°F (66°C)		X (S)
1 hrs at 200°F (93°C)		X (U)
1 hrs at 250°F (121°C)		X (U)

S = Supported U = Unsupported

In General

Tool, mould and/or pattern preparation:

Wood structures should be sealed. Gypsum moulds should be dried to remove free moisture and preferably sealed with a PFP process or appropriate sealer. All non-porous tools, moulds or patterns should be treated with release or parting agents which can withstand the temperature that the part will be cured at while remaining in a supported position.

Storage

Store at 60-100°F in a dry place. After use, tightly reseal. (This product may crystallise during storage. If crystallised, vent container and heat to 125-145°F until crystals dissolve. Stir well after product has been liquefied.) Always use clean dry tools for mixing and applying. Mix according to the mix ratio stated for the specific product as listed on the front page. Mix together thoroughly and use immediately. Material temperatures should not be below 65°F when mixing.

Safety Measures

Work in well ventilated areas using gloves, eye protection and clothing protection. Avoid contact to the skin and eyes. Avoid clothing contamination. Wash thoroughly after handling. These products may cause skin and respiratory allergic reactions. Consult the Material Safety Data Sheets for complete precautions with this product.

The information given within this document is of a general nature only. The values given must be considered as typical and do not constitute a product specification. No liability for loss or damage can be accepted by Trelleborg Offshore UK Ltd. or ebalta UK Ltd. Unless otherwise stated, all properties are quoted at ambient conditions. All information contained herein is the proprietary information of Trelleborg Offshore UK Ltd. and must not be copied or disclosed to any other party without the prior written permission of Trelleborg Offshore UK Ltd. The information contained herein must only be used for the Specific Purpose for which it was provided.

ebalta UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT
 t: +44 1332 814700 . f: +44 1332 814775 . e: info@ebalta.co.uk . w: www.ebalta.co.uk